

# **GA-91\*1** series heat cure rubber

30-70hardness shoreA, DBPMH, antistatic precipitated silicone rubber

#### Feature

- Good antistatic effect
- Odorless

# Application

- Rubber roll
- Electric product sheath
- Good anti-yellowing property

Typical characteristics					
Product code	GA-9131	GA-9141	GA-9151	GA-9161	GA-9171
Appearance	Transparent				
William plasticity	120	140	200	240	270
Hardness(ShoreA)	30	40	50	60	70
Density(g/cm <sup>3</sup> )	1.11	1.14	1.17	1.18	1.19
Tensile strength(Mpa)	7.0	8.0	8.5	8.5	8.0
Elongation(%)	700	600	550	500	450
Tear strength(KN/m)	15	18	20	20	25
Surface resistance(Ω)				1011	

# Remark:

1. The above data obtained from through using 1.0% of 50% of preoxide(DBPMH) in pressurized solidification for 5 minutes at 175℃ to make a 2 mm thickness specimen.

2、 the above data is not for specification customized, before make this product specification, please contact genvan sales person.

# Description

GA-91\*1 series product have good antistatic effect, odorless, yellowing change small after post cure. Product contact with food need to do two-process treatment at 200°C 4hours.



#### Application, coloring, modifying, mixing

Product can be colored, keep the color of the pigment itself.

can use Genvan' s additive to change the properties,like aging resistance,compression deformation of the product,more detailed info. for how to use the additives,please contact Genvan company local sales or customer service.

### Storage&period of validity

The product is stored unopened at 50°C or below the shelf life is 6 months from the date of production;

Out of the expiration date, it shall be fully tested. determine to meet the customer's own product specifications, only continue to use

#### Package

The product by standard measurement, plastic film packaging, for 20kgs/ box.Samples available

#### **Product safety info.**

This information does not include safety info. for how to use this product safely.

Please read product, safety data sheet, labels on product packing container before operation.

For safety data sheet, can log in <u>www.genvan.com</u> to download or obtain from Genvan company sales person.



#### Limited warranty information - please read carefully

◆Based on the premise of good faith, provided here information should be considered accurate.However,
Due to the condition and method of using our company product is beyond our control. This information can not replace the relevanted testing from customer to assure our company product safety, effective,and fully meet final application.The using suggestions we offered ,can not be deemed to infringe any patent right's reason.

◆Genvan's only guarantee is the company's products in all the necessary tests were carried out before shipment the test data conform to the factory standard.

◆Genvan emphasizes that no any promise of compensation for any indirection or attachment damage incurred

◆Due to different testing production conditions, we cannot make sure we both get the same test results users are advised to use their own testing conditions to get the data as the using performance properties.

◆Any of the above performance data and applicable recommendations, only is one of use references for the performance of Genvan products instead of the guarantee for the effectiveness or universality of Genvan products in a particular application

•We reserve the right to change the parameters of the product without further notice.